

Project:

Order No: Premio EPS100 Compression test

Part No: P100/2018_11_15(1)


Customer: Premio Hungária

Tester: Thümler GmbH-Z5

Method: MSZ EN 826

Execution date: 2018. 11. 15. 13:15:47

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P100/2018_11_15(4)	109,62	9,99
P100/2018_11_15(5)	107,91	9,99
P100/2018_11_15(6)	102,88	9,99
P100/2018_11_15(7)	104,96	9,98
Max.	109,62	9,99
Min.	102,88	9,98
Mean	106,34	9,99