

Project:

Order No: Premio EPS80 Compression test

Part No: P80/2019_04_29


Customer: Premio Hungária

Tester: Thümler GmbH-Z5

Method: MSZ EN 826

Execution date: 2019. 04. 29. 17:30:38

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P80/2019_04_29 (1)	87,85	9,99
P80/2019_04_29 (2)	88,24	10,00
P80/2019_04_29 (3)	89,67	9,98
P80/2019_04_29 (4)	87,71	9,99
Max.	89,67	10,00
Min.	87,71	9,98
Mean	88,37	9,99