

Project:

Order No: Premio EPS80 Compression test

Part No: P80/2020_06_15(1)


Customer: Premio Hungária

Tester: Thümler GmbH-Z5

Method: MSZ EN 826

Execution date: 2020. 06. 15. 12:55:12

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P80/2020_06_15 (1)	86,50	10,00
P80/2020_06_15 (2)	87,88	9,99
P80/2020_06_15 (3)	86,97	9,99
P80/2020_06_15 (4)	84,58	10,00
Max.	87,88	10,00
Min.	84,58	9,99
Mean	86,48	9,99